

Birch Ply

Form Form L



Metsä Wood Form is birch plywood, in which both sides are overlaid with phenol film and the edges are sealed. Form plywood is an ideal formwork panel for smooth surfaced concrete elements. It can also be used as a multipurpose, maintenance-free panel for various other uses. Metsä Wood Form is available in sizes standard, L, XL and KingSize.

Applications

Concrete Formwork:

Metsä Wood Form is a smooth surface maintenance-free panel for different concrete formwork uses: system shuttering, girder formwork, regeneration panels, element industry and concrete block industry.

The durable overlays ensure smooth concrete cast finish and multiple uses. The number of uses can rise up to 30 –100 but is highly dependent on the used overlay, site practice, requirements of concrete finish, the quality of release agent and the maintenance, handling and storage practices.

Use high quality release agent to ensure easier and cleaner release. Make sure that the release agent is suitable with the panel overlay. Clean panels after each use to remove all concrete debris. Seal scratches with water proof paint and fill holes with water resistant filler. Afterwards, apply a fresh coat of release agent prior to each subsequent use.

Other Applications:

Metsä Wood Form is a general panel used in variety of applications

- Transport industry: Transport equipment, containers, trailer side boards, sliding doors, vehicle and flight cases and other transport boxes, bus floor constructions etc.

- Building applications: Agricultural structures, general interior and covered exterior building applications
- Other applications: Packaging applications, sport arenas and equipment

Major advantages

- **Smooth durable overlay**
- **Excellent strength-to-weight ratio**
- **Dimensionally stable**
- **Strong and rigid**
- **Easy to clean and re-use**
- **Easy to machine and fasten using conventional woodworking tools and fasteners**
- **Can withstand impacts and other forms of bruising**
- **Environmentally friendly**
- **Weather- and boil-proof bonding**

Birch Ply

Form Form L

Base plywood

The base plywood of Metsä Wood Form is Metsä Wood Birch. Birch plywood is made of cross-bonded 1.4 mm thick birch veneers bonded with weather- and boil-resistant phenol formaldehyde adhesive.

Designed and tailor-made to serve in demanding applications, birch plywood can be ordered with special oriented veneer structures to provide even higher strength and stiffness properties.

Overlay

A smooth and durable phenolic film is hot-pressed onto the panel surface. The film consists of special base papers impregnated with phenolic resin. A film with a basis weight of 120 g/m² is normally used. With Form L minimum film weight is 220 g/m². Thicker overlays are available on request. Standard film colours for Form and Form L are dark brown and grey. Light brown, yellow and black colours are available for Form on request. The phenol film is not UV resistant and the colour may change when exposed to sunlight over prolonged periods.

Surface properties

The film surface is semi-glossy, smooth, hard and slippery. It withstands abrasion, is moisture-resistant and can tolerate commonly used chemicals as well as diluted acids and alkalis. The surface is easy to clean with water or steam. Moisture absorption is minimal.

ABRASION RESISTANCE*

	OVERLAY WEIGHT	TABER REVOLUTIONS**
Form (dark brown)	120 g / m ²	350
Form (dark brown)	220 g / m ²	700
Form (dark brown)	440 g / m ²	1,500
Form (grey)	220 g / m ²	700

* Values are indicative and valid for new unused panels

** Abrasion resistance is tested according to EN 438-2 / DIN 53799

Edge sealing

Panel edges are sealed against moisture absorption with acrylic edge sealing paint. The standard colours of the edge sealing are dark brown and grey. Even though edge sealing slows down the absorption of moisture into the wood, it does not eliminate it completely.

Panel sizes

	WIDTH (mm)	2,400	2,440	2,500	3,000	3,050	3,660	4,110
	LENGTH (mm)							
Form	1,200*	■	■	■	■	■	■	■
	1,220*	■	■	■	■	■	■	■
	1,250*	■	■	■	■	■	■	■
	1,500*	■	■	■	■	■	■	■
	1,525*	■	■	■	■	■	■	■
Form L	1,870*	■	■	■	■	■	■	■
	2,020*	■	■	■	■	■	■	■

* The measurement indicates the orientation of the surface veneer grain.

■ = standard panel size with dark brown overlay

■ = standard panel size with grey overlay

■ = available on request

Other sizes are available on request. Larger size scarf-jointed XL and KingSize panels are also available by special order.

Size tolerances

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet EN 315 requirements.

PANEL TOLERANCES

LENGTH / WIDTH	TOLERANCE
< 1,000 mm	±1 mm
1,000-2,000 mm	±2 mm
> 2,000 mm	±3 mm
Squareness	±0.1 % or ±1 mm/m
Edge straightness	±0.1 % or ±1 mm/m

Thicknesses, structures and thickness tolerances

The thickness tolerances fulfil the requirements of standard EN 315 and are in part more stringent than the official requirements.

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS *

NOMINAL THICKNESS (mm)	NUMBER OF PLIES (pcs)	THICKNESS TOLERANCE		WEIGHT (kg/m ²)
		min. (mm)	max. (mm)	
6.5	5	6.1	6.9	4.4
9	7	8.8	9.5	6.1
12	9	11.5	12.5	8.2
15	11	14.3	15.3	10.2
18	13	17.1	18.1	12.2
21	15	20.0	20.9	14.3
24	17	22.9	23.7	16.3
27	19	25.2	26.8	18.4
30	21	28.1	29.9	20.4
35	25	33.5	35.5	23.8

* Moisture content of the product affects its dimensions

* Average density of Metsä Wood birch plywood is 680 kg/m³ (at relative humidity of RH 65 %)

* Special structures and thicknesses are available on request

* Customised tolerances are possible but must be agreed separately

Bonding classes

Metsä Wood plywood panels are bonded with a weather- and boil-resistant phenol formaldehyde adhesive. The gluing meets the requirements of the standard EN 314-2 / Class 3 (exterior).

Formaldehyde emissions

Determined according to EN 717-1, the formaldehyde emitted by Metsä Wood Form falls far below the Class E1 requirement of ≤ 0.100 ppm and fulfils also the most stringent requirements in the world (≤ 0.030 ppm). The formaldehyde emission of Metsä Wood Form is approximately 0.017 ppm.

>>

Birch Ply

Form
Form L

Panel strength properties

Metsä Wood Form is a CE marked product and its strength and elasticity properties are identical with the Metsä Wood Birch standard plywood properties. The properties are specified according to standards EN 789 and EN 1058 and can be found in the Metsä Wood Form Declaration of Performance (DoP). DoP documents can be downloaded from www.metsawood.com/dop.

The Concrete formwork design data (permissible concrete pressure tables, design nomograms) for all Metsä Wood formwork panels can be found in Metsä Wood Concrete Formwork technical data.

Machining

Metsä Wood Form plywood panels can be machined according to customer specification on request.

Packing

Metsä Wood Form panels are packed in moisture-resistant plastic wrapping.

PACKING QUANTITIES

PANEL SIZE (mm)	NUMBER OF PANELS PER PALLET BY THICKNESS								
	6.5	9	12	15	18	21	24	27	30
1,500 / 1,525 x 2,400 – 3,660	90	65	50	40	35	30	25	25	20
1,200/1,220/1,250 x 2,850 – 3,660									
1,500/1,525 x 1,500 – 2,135	140	100	75	60	50	45	40	35	30
1,200/1,220/1,250 x 1,200 – 2,800									
1,500/1,525 x 3,670 – 4,110	70	50	35	30	25	20	15	15	15
1,870/2,020 x 1,870 – 4,110									
1,870 / 2,020 x 1,870 / 2,020	140	100	70	60	50	40	30	30	30

Further information

- Metsä Wood Form Declaration of Performance (www.metsawood.com/dop)
- Metsä Wood Concrete Formwork brochure
- Metsä Wood Concrete Formwork technical data
- Metsä Wood Form XL Product Data Sheet
- Metsä Wood KingSize Product Data Sheet

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves the right to make alterations to its products, product information and product range without prior notice.