

Birch Ply

Flex XL



Metsä Wood Flex XL is a larger size birch plywood panel overlaid with a coloured thermoplastic overlay which is UV-resistant. The combination of technical properties with high class surfaces makes Flex XL an excellent panel for various applications. XL panels enable larger one piece components.

APPLICATIONS

Metsä Wood Flex XL provides a larger size easy ready finished surface solution.

- **Transport industry:** Side walls for horse and box trailers, side walls for light and medium size trucks, doors bulk heads, van linings and transit and flight cases
- **Building industry:** Furniture, shop, kitchen and sanitary fittings, playground equipment, fencing and rebound walls

MAJOR ADVANTAGES

- **High quality surfaces**
- **Excellent impact and crack resistance**
- **Good weather resistance**
- **Easy to fix and cut**
- **Excellent wear resistance**
- **Easy to clean**
- **Good resistance against most chemicals**
- **Strong and rigid panel**
- **Excellent strength-to-weight ratio**
- **Dimensionally stable**
- **Made of sustainable Nordic wood and PEFC (PEFC/02-31-381) certified**

Birch Ply

Flex XL

BASE PLYWOOD

The base plywood of Metsä Wood Flex XL is Metsä Wood Birch. Birch plywood is made of cross-bonded 1.4 mm thick birch veneers bonded with weather- and boil-resistant phenol formaldehyde adhesive. The core panel of the large size Flex XL is scarf-jointed from standard size birch plywood panels using melamine urea formaldehyde or phenol resorcinol formaldehyde adhesive.

OVERLAY

Flex O6 overlay

The panel is overlaid with coloured, 0.6 mm thick structured (burl) polypropylene overlay.

The overlay is bonded to plywood with water resistant adhesive. Metsä Wood Flex XL is available in colour WhiteO6 (RAL 9016).

SURFACE PROPERTIES

The surface of the overlay is structured to improve wear and scratch resistance. Overlay is elastic, tough and does not crack easily. It is also moisture and UV-resistant. The overlay is safe to use and it is free of chlorine, halogens, plasticizer, formaldehyde and heavy metals.

The surface is easy to clean with water and normal detergents. Strong acids, alkalis and e.g. acetone may cause visual changes on the surface.

Metsä Wood Flex XL plywood products have very high surface quality and the surface is susceptible to scratches due to its softer appearance, extra caution has to be practised in handling and storing the panels to prevent damage. Extreme moisture penetration may cause visible changes on the appearance of the product.

Technical properties of surface

- Taber value is approx 10 000 R*
- Colour stability 6-7 according to DIN 54404
- Colour change $\Delta E < 1.5$ according to ISO 4892-2 (600 h)
- Crack resistance EN 13696 no cracks
- Impact resistance Class IC3 according to EN 438-2

* Abrasion resistance is tested according to EN 438-2 / DIN 53799

EDGE SEALING

Panel edges are sealed against moisture absorption with edge sealing paint. The standard colour of the edge sealing is transparent. Even though edge sealing slows down the absorption of moisture into the panel, it does not eliminate it completely.

PANEL SIZES

Metsä Wood Flex XL O6 is available in sizes:

- XL 6 000 mm x 1 800 / 1 900 mm
- XL 6 000 mm x 2 000 / 2 150 mm

The first measurement indicates the orientation of the surface veneer grain.

Other sizes are available on request.

SIZE TOLERANCES

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet EN 315 requirements.

PANEL TOLERANCES

LENGTH / WIDTH	TOLERANCE
< 1 000 mm	± 1 mm
1 000 - 2 000 mm	± 2 mm
> 2 000 mm	± 3 mm
Squareness	± 0.1 % or ± 1 mm/m
Edge straightness	± 0.1 % or ± 1 mm/m

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS*

NOMINAL THICKNESS	NUMBER OF PLYS	THICKNESS TOLERANCE		WEIGHT
(mm)	(ant.)	min. (mm)	max. (mm)	kg/m ²
12	9	11.5	13.1	8.7
15	11	14.3	15.9	10.7
18	13	17.1	18.7	12.7
21	15	20.0	21.5	14.8
24	17	22.9	24.3	16.8
27	19	25.2	27.4	18.9
30	21	28.1	30.5	20.9

* The moisture content of the product affects its dimensions

* Average density of Metsä Wood Spruce plywood is 680 kg/m³ (at a relative humidity of 65%)

* Special structures and thicknesses are available on request

* Customised tolerances are possible but must be agreed separately

BONDING CLASSES

Metsä Wood plywood panels are bonded with a weather- and boil-resistant phenol formaldehyde adhesive. The gluing meets the requirements of the standard EN 314-2 / Class 3 (exterior).

The scarf joint is glued with melamine urea formaldehyde or phenol resorcinol formaldehyde adhesive. The overlay is bonded to plywood with weather resistant adhesive (EN 204 class D4).

FORMALDEHYDE EMISSIONS

Determined according to EN 717-1, the formaldehyde emissions of Metsä Wood Flex are well below the Class E1 requirement of ≤ 0.100 ppm. The product complies with Commission Regulation (EU) 2023/1464, and the formaldehyde emission is below the specified limit of 0.062 mg/m³.

Birch Ply

Flex XL

APPROVALS AND DESIGN PROPERTIES

Due to the scarf jointed core plywood, the strength values of Metsä Wood Flex XL in the longitudinal direction of the panel are ca. 65% of standard Metsä Wood Birch plywood values. In the cross direction of the panel the strength values are similar to standard Birch plywood. Stiffness values in both directions are similar to standard Birch plywood.

Birch plywood production is managed according to the principles of standard ISO 9001. The quality and the constancy of performance of the product is controlled by regular third party inspections and audits.

MECHANICAL PROPERTIES*

THICKNESS* (mm)	MEAN MODULUS OF ELASTICITY** (N/mm ²)		CHARACTERISTIC BENDING STRENGTH** (N/mm ²)	
		⊥		⊥
12	10719	6781	27.9	33.2
15	10316	7184	26.8	33.8
18	10048	7452	26.1	34.1
21	9858	7642	25.6	34.3
24	9717	7783	25.3	34.4
27	9607	7893	25.0	34.5
30	9519	7981	24.8	34.6

* Moisture content 12%

** Properties determined according to EN 789 standard

MACHINING

Metsä Wood Flex XL plywood panels can be machined according to customer specification on request.

PACKAGING

Metsä Wood Flex XL panels are packed in moisture-resistant plastic wrapping.

PACKING QUANTITIES

PANEL SIZE (mm)	NUMBER OF PANELS PER PALLET BY THICKNESS						
	12	15	18	21	24	27	30
6000 x 1800 / 1900	Packet sizes agreed case by case						
6000 x 2000 / 2150	Packet sizes agreed case by case						

FURTHER INFORMATION

- Metsä Wood Flex Product Data Sheet

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves the right to alteration of its products, product information and product range without any notice.

06/2026