

Birch Ply

Metsä Wood DURAForm®



Metsä Wood DURAForm is a high performance formwork panel choice for smooth surfaced concrete elements. Metsä Wood DURAForm plywood has a special treatment to resist the surface rippling that ensures smooth high quality concrete finish from the first pour. Metsä Wood DURAForm panel surface is a multi-material composite that is harder and more scratch and wear-resistant than standard formwork panels.

APPLICATIONS

Metsä Wood DURAForm is a smooth surface, maintenance-free birch plywood panel for different concrete formwork applications: system shuttering, girder formwork, regeneration panels, element industry and concrete block industry.

The hard composite surface of Metsä Wood DURAForm ensures smooth concrete finish and multiple uses. The number of uses can rise up to 200 but is highly dependent on the site practice, requirements of concrete finish, the quality of release agent and the maintenance, handling and storage practices.

Use high quality release agent to ensure easier and cleaner release. Make sure that the release agent is suitable with the panel overlay. Clean panels after each use to remove all concrete debris. Seal scratches with water proof paint and fill holes with water resistant filler. Afterwards, apply a fresh coat of release agent prior to each subsequent use.

MAJOR ADVANTAGES

- Extra hard and wear-resistant surface
- Surface resists rippling
- Smooth durable multi-material composite surface
- Easy to clean and re-pour up to 200 times
- Can withstand impacts and other forms of bruising
- Dimensionally stable
- Strong and rigid
- Made of sustainable Nordic wood and PEFC (PEFC/02-31-03) certified

BASE PLYWOOD

The base plywood of Metsä Wood DURAForm is Metsä Wood Birch. Birch plywood is made of cross-bonded 1.4 mm thick birch veneers bonded with weather- and boil-resistant phenol formaldehyde adhesive.

Designed and tailor-made to serve in demanding applications, birch plywood can be ordered with special oriented veneer structures to provide even higher strength and stiffness properties.

SURFACE PROPERTIES

The outermost smooth and durable surface of the multi-material composite is created by hot pressing special impregnated paper onto the panel surface. The composite is moisture-resistant and therefore reduces surface rippling and provides a smooth concrete cast from the first use. The composite structure for casting is applied only to the concrete side of the panel.

On the backside of the panel, the overlay has Metsä Wood DURAForm logo imprinted into the panel surface. Film colour is dark brown. The phenol film is not UV resistant and the colour may change when exposed to sunlight over prolonged periods.

ABRASION RESISTANCE*

	TABER REVOLUTIONS**
DURAForm	1750

* Values are indicative and valid for new unused panels

** Abrasion resistance is tested according to EN 438-2 / DIN 53799

EDGE SEALING

Panel edges are sealed against moisture absorption with acrylic edge sealing paint. Even though edge sealing slows down the absorption of moisture into the wood, it does not eliminate it completely.

PANEL SIZES

	LENGTH (mm)	WIDTH (mm)				
		2440	2500	3000	3050	3660
DURAForm	1200*	■	■	■	■	■
	1220*	■	■	■	■	■
	1250*	■	■	■	■	■
	1500*	■	■	■	■	■
	1525*	■	■	■	■	■

* The measurement indicates the orientation of the surface veneer grain.

■ = standard panel size

Other sizes are available on request.

SIZE TOLERANCES

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet EN 315 requirements.

PANEL TOLERANCES

LENGTH / WIDTH	TOLERANCE
< 1 000 mm	± 1 mm
1 000 - 2 000 mm	± 2 mm
> 2 000 mm	± 3 mm
Squareness	± 0.1 % or ± 1 mm/m
Edge straightness	± 0.1 % or ± 1 mm/m

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES

The thickness tolerances fulfil the requirements of standard EN 315 and are in part more stringent than the official requirements.

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS*

NOMINAL THICKNESS (mm)	NUMBER OF PLYS (no.)	THICKNESS TOLERANCE		WEIGHT (kg/m ²)
		min. (mm)	max. (mm)	
12	9	11.5	12.5	8.2
15	11	14.3	15.3	10.2
18	13	17.1	18.1	12.2
21	15	20.0	20.9	14.3

* Moisture content of the product affects its dimensions

* Average density of Metsä Wood birch plywood is 680 kg/m³ (at relative humidity of RH 65 %)

* Special structures and thicknesses are available on request

* Customised tolerances are possible but must be agreed separately

BONDING CLASSES

Metsä Wood plywood panels are bonded with a weather- and boil-resistant phenol formaldehyde adhesive. The gluing meets the requirements of the standard EN 314-2 / Class 3 (exterior).

APPROVALS AND DESIGN PROPERTIES

Metsä Wood DURAForm strength and elasticity properties are identical with the Metsä Wood Birch standard plywood properties. The properties are specified according to standard EN 13986 and can be found in the Metsä Wood Birch Declaration of Performance (DoP). DoP documents can be downloaded from www.metsawood.com/dop.

The Concrete formwork design data (permissible concrete pressure tables, design nomograms) for all Metsä Wood formwork panels can be found in Metsä Wood Concrete Formwork technical data.

Birch plywood production is managed according to the principles of standard ISO 9001. The quality and the constancy of performance of the product is controlled by regular third party inspections and audits.

MACHINING

Metsä Wood DURAForm plywood panels can be machined according to customer specification on request.

PACKAGING

Metsä Wood DURAForm panels are packed in moisture-resistant plastic wrapping.

PACKING QUANTITIES

PANEL SIZE (mm)	NUMBER OF PANELS PER PALLET BY THICKNESS			
	12	15	18	21
1500/1525 x 2440-3660				
1200/1220/1250 x 3000-3660	50	40	35	30
1500/1525 x 1500-2135				
1200/1220/1250 x 1200-2750	70	60	50	45

FURTHER INFORMATION

- Metsä Wood Birch Declaration of Performance (www.metsawood.com/dop)
- Metsä Wood Concrete Formwork brochure
- Metsä Wood Concrete Formwork technical data

Metsä Wood does not sell, market or distribute the product and does not allow anyone else to do the same under the mark "Metsä Wood DURAForm" or "DURAForm" in the United States of America or Canada.

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves the right to alteration of its products, product information and product range without any notice.