

# MetsäBoard Pro FBB OBAfree

## PRODUCT SHEET



### Product description

Fully coated folding boxboard, hard sized, OBA free


### End use

Foods, Healthcare, Frozen food, Chilled food, Plates, Trays, Folded trays, Fast food applications, Food service, Beverages, General packaging

### Features

Printing method Flexo, Offset, Digital  
 Food contact EU Regulation (EC) No 1935/2004, GB4806.8, GB9685, USFDA21CFR§176.170\*, USFDA21CFR§176.180\*  
 Metsä Board mill Husum

### Structure



- 1) Double blade coating
- 2) Bleached chemical pulp
- 3) Bleached chemi-thermo-mechanical pulp (BCTMP)
- 4) Bleached chemical pulp

PROPERTY, UNIT	METHOD	STANDARD	TOLERANCE	190	215	225	240	260	275	285	315	345
Grammage g/m <sup>2</sup>		ISO 536	± 2%									
Thickness µm		ISO 534	± 3%	305	355	385	415	455	485	505	555	610
Bending stiffness CD	Taber 15°	ISO 2493-2	- 15%	3.6	5.3	6.3	7.8	9.7	11.3	12.5	16.0	19.2
Bending stiffness MD	Taber 15°	ISO 2493-2	- 15%	7.3	10.6	12.5	15.7	19.5	22.5	25.0	32.7	38.2
Moisture content %		ISO 287	± 1.0	7.0	7.0	7.2	7.5	7.7	7.8	8.1	8.3	8.5
Smoothness top µm	PPS10	ISO 8791-4	max 1.6	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4
Brightness top %	Illumination C/2°	ISO 2470-1	± 1	85	85	85	85	85	85	85	85	85
Off-flavour (Robinson test)	12 mo in orig. pack	EN 1230-2		< 1	< 1	< 1	< 1	< 1	< 1	< 1	< 1	< 1

Tolerances, when specified, are based on 95% confidence limits on mill measurements of samples tested in standard conditions (23°C/50% RH).

Metsä Board Paperboard mills have FSC® / C001580 and PEFC / 02-31-92 CoC certificates.

\*Please contact Metsä Board for details of grammage and / or country-specific, restrictions and limitations.

Issued 18.05.2026. Supersedes sheet dated 03.03.2026.