

Spruce Ply

MouldGuard



Metsä Wood Spruce MouldGuard is a surface impregnated softwood plywood that significantly reduces the risk of mould growth compared to unprotected softwood plywood. The product provides a ready-to-use surface in humid conditions, with a natural visual quality.

APPLICATIONS

Metsä Wood Spruce MouldGuard is a multi-purpose construction panel for conditions where the relative humidity may exceed 75%. It can be used in the same way as standard Metsä Wood Spruce plywood, but it should be protected from direct rain and UV radiation. Direct contact with foodstuffs, animal feed or similar must be avoided.

- **Building applications:** roof, floor and wall structures, agricultural buildings, attics, roof overhangs etc.
- **Renovation:** repairing, improving and renovating buildings
- **In general:** applications with a risk of increased humidity, such as unheated buildings and structures, e.g. garages, roof panels

MAJOR ADVANTAGES

- **Improved resistance to mould and blue stain in humid conditions**
- **Ready-to-use surface saves time at the construction site**
- **Strong, rigid and lightweight**
- **Easy to machine and install using conventional woodworking tools and fasteners**
- **Panel is impact resistant and does not crumble**
- **Good base for fasteners**
- **Weather- and boil-proof bonding**
- **Available with square edge and tongue-and-groove profiles**
- **Made of sustainable Nordic wood and PEFC (PEFC/02-31-381) certified**

Spruce Ply

MouldGuard

BASE PLYWOOD

The base plywood of Metsä Wood Spruce MouldGuard is Metsä Wood Spruce, which is made of cross-bonded 3 mm thick coniferous veneers and bonded with a weather- and boil-resistant phenol formaldehyde adhesive.

SURFACE PROPERTIES

Metsä Wood Spruce MouldGuard panels have a light brown colour. The surface can be unsanded or sanded on both sides. Additional coatings are not recommended for Metsä Wood Spruce MouldGuard.

The surface grades are determined by the grade of the surface veneers as follows:

Spruce plywood surfaces -Typical properties
III – standard quality, with open defects such as knotholes and veneer checks.

Classification of Metsä Wood Spruce surface grade meets the requirements of EN 635.

PANEL SIZES

Metsä Wood Spruce MouldGuard is available in sizes:

- 2400 / 2440 / 2500 mm x 1200 / 1220 / 1250 mm
- 2400 / 2440 mm x 600 / 610 mm

The first measurement indicates the orientation of the surface veneer grain.

Other sizes are available on request.

SIZE TOLERANCES

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet the requirements of EN 315.

PANEL TOLERANCES

LENGTH / WIDTH	TOLERANCE
< 1 000 mm	± 1 mm
1 000 - 2 000 mm	± 2 mm
> 2 000 mm	± 3 mm
Squareness	± 0.1 % or ±1 mm/m
Edge straightness	± 0.1 % or ±1 mm/m

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES

The thickness tolerances fulfil the requirements of standard EN 315 and are, in part, more stringent than the official requirements.

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS*

NOMINAL THICKNESS (mm)	NUMBER OF PLYS (no.)	THICKNESS TOLERANCE		WEIGHT kg/m ²
		min. (mm)	max. (mm)	
9	3	8.8	9.5	4.1
12	4	11.5	12.5	5.5
15	5	14.3	15.3	6.9
18	6	17.1	18.1	8.3
21	7	20.0	20.9	9.7
24	8	22.9	23.7	11.0
27	9	25.2	26.8	12.4
30	10	28.1	29.9	13.8

* The moisture content of the product affects its dimensions

* Average density of Metsä Wood Spruce plywood is 460 kg/m³ (at a relative humidity of 65%)

* Special structures and thicknesses are available on request

* Customised tolerances are possible but must be agreed separately

PERFORMANCE AGAINST MOULD GROWTH

Metsä Wood Spruce MouldGuard is surface impregnated with a wood preservative. According to the third party test results, the mould and blue stain resistance of Spruce MouldGuard is significantly better (4-5 times) than standard Metsä Wood Spruce plywood.

The preservative is classified for hazard class 3 (EN 599-1). The efficiency of the chemical has been verified according to the EN 113 (decay) and EN 152-1 (blue stain) tests.

Production of Spruce MouldGuard is controlled by Eurofins Expert Services Oy.

Biocidal Products Regulation (EU) No 528/2012

Spruce MouldGuard is treated with biocide:

- preservative surface treatment reduces the risk of mould growth and blue stain
- active substances: propiconazole, 3-iodo-2-propynyl butylcarbamate
- direct contact to foodstuffs or animal feed should be avoided
- shall not be used for the production of furniture and play structures.

BONDING CLASSES

Metsä Wood plywood panels are bonded with a weather- and boilresistant phenol formaldehyde adhesive. The gluing meets the requirements of the standard EN 314-2 / Class 3 (exterior).

FORMALDEHYDE EMISSIONS

Determined according to EN 717-1, the formaldehyde emissions of Metsä Wood Spruce are well below the Class E1 requirement of ≤ 0.100 ppm. The product complies with Commission Regulation (EU) 2023/1464, and the formaldehyde emission is below the specified limit of 0.062 mg/m³.



Spruce Ply

MouldGuard

APPROVALS AND DESIGN PROPERTIES

Metsä Wood Spruce MouldGuard is CE and UKCA marked and the design properties are determined according to standard EN 13986. The design properties given in the Declaration of Performance (DoP) and in the UK Declaration of Conformity (UK DoC) are to be used for structural calculations with EN 1995 (Eurocode 5). The DoP documents can be downloaded from www.metsawood.com/dop and the UK DoC documents can be downloaded from www.metsawood.com/ukdoc.

Metsä Wood Spruce MouldGuard has also national approval in Norway.

Spruce plywood production is managed according to the principles of standard ISO 9001. The quality and the constancy of performance of the product is controlled by regular third party inspections and audits.

MACHINING

Metsä Wood Spruce MouldGuard panels can be delivered with tongue-and-groove edge machining on either two sides or four sides. Tongue-and-groove panels are always sanded. Tongue-and-groove machining decreases net panel size by 10mm. Tongue-and-groove machining is available for panel thicknesses ≥ 12 mm.

PACKAGING

Metsä Wood Spruce MouldGuard panels are packed in moisture resistant plastic wrapping.

PACKING QUANTITIES

PANEL SIZE (mm)	NUMBER OF PANELS PER PALLET BY THICKNESS							
	9	12	15	18	21	24	27	30
2400/2440/2500 x 1200/1220/1250	110	85	65	55	45	40	35	30

PRODUCT DISPOSAL

Metsä Wood Spruce MouldGuard can be considered a biofuel (EN 14961-1) and it can be safely burnt when the combustion temperature is at least 850 °C and the correct combustion conditions are maintained. Due to the preservative treatment, the correct combustion conditions and suitable waste-burning plants should be checked locally.

FURTHER INFORMATION

- Metsä Wood Spruce MouldGuard Declaration of Performance (www.metsawood.com/dop)
- Metsä Wood Spruce MouldGuard the UK Declaration of Conformity (www.metsawood.com/ukdoc)
- Metsä Wood Spruce Plywood Manual
- Metsä Wood Spruce Plywood for Construction brochure

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves the right to alteration of its products, product information and product range without any notice.

06/2026