

DECLARATION OF PERFORMANCE

NO. MW/LVL/313-001/CPR/DOP



1. **PRODUCT-TYPE:**
 Kerto LVL Qp-beam
 Structural Laminated Veneer Lumber, with crosswise veneers (LVL-C)

THICKNESS	NUMBER OF VENEERS	LONG GRAINED	CROSS GRAINED	LAY-UP
39 mm	13	11	2	- -
42 mm	14	12	2	- -
45 mm	15	13	2	- -
48 mm	16	14	2	- -
51 mm	17	15	2	- -
54 mm	18	16	2	- -
57 mm	19	17	2	- -
60 mm	20	18	2	- -
63 mm	21	19	2	- -
66 mm	22	20	2	- -
69 mm	23	21	2	- -
72 mm	24	22	2	- -
75 mm	25	23	2	- -

2. **INTENDED USES:**
 Buildings and bridges

3. MANUFACTURER:

Metsäliitto Cooperative
Metsä Wood
P.O.Box 24
FI-08101 Lohja, Finland
Tel. +358 10 4605
metsagroup.com/metsawood/

5. SYSTEM OF ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE:

AVCP System 1

6a. HARMONISED STANDARD:

EN 14374:2004

Notified body:

Eurofins Expert Services Oy, Notified product certification body No. 0809

Certificate of constancy of performance:

0809 – CPR – 1002

7. DECLARED PERFORMANCES

ESSENTIAL CHARACTERISTICS	SYMBOL	PERFORMANCE	
		KERTO LVL Qp-beam THICKNESS 39 - 51 mm	KERTO LVL Qp-beam THICKNESS 54 - 75 mm
Modulus of elasticity and shear modulus		N/mm² or kg/m³	N/mm² or kg/m³
<u>Modulus of elasticity, mean values</u>			
Parallel to grain, along	$E_{0,mean}^2$	11700	12300
Parallel to grain, along, flatwise	$E_{m,0,flat,mean}$	11300	11400
Parallel to grain, across	$E_{m,90,flat,mean}$	NPD	NPD
Perpendicular to grain, edgewise	$E_{c,90,edge,mean}^4$	NPD	NPD
Perpendicular to grain, flatwise	$E_{c,90,flat,mean}$	NPD	NPD
<u>Modulus of elasticity, fifth percentile value</u>			
Parallel to grain, along	$E_{0,k}^3$	9800	10300
Parallel to grain, along, flatwise	$E_{m,0,flat,k}$	9500	9600
Parallel to grain, across	$E_{m,90,flat,k}$	NPD	NPD
Perpendicular to grain, edgewise	$E_{c,90,edge,k}^5$	NPD	NPD
Perpendicular to grain, flatwise	$E_{c,90,flat,k}$	NPD	NPD
<u>Shear modulus, mean values</u>			
Edgewise	$G_{0,edge,mean}$	600	600
Flatwise, parallel to grain	$G_{0,flat,mean}$	120	120
Flatwise, perpendicular to grain	$G_{90,flat,mean}$	NPD	NPD
<u>Shear modulus, fifth percentile value</u>			
Edgewise	$G_{0,edge,k}$	400	400
Flatwise, parallel to grain	$G_{0,flat,k}$	100	100
Flatwise, perpendicular to grain	$G_{90,flat,k}$	NPD	NPD
Strength, fifth percentile values			
<u>Bending strength</u>			
Edgewise (depth 300mm)	$f_{m,0,edge,k}$	36.0	38.0
Size effect parameter	s	0.12	0.12
Flatwise, parallel to grain	$f_{m,0,flat,k}$	36.0	36.0
Flatwise, perpendicular to grain	$f_{m,90,flat,k}$	NPD	NPD
<u>Compression strength</u>			
Parallel to grain	$f_{c,0,k}$	28.0 ¹	30.0 ¹
Perpendicular to grain, edgewise	$f_{c,90,edge,k}$	6.0	6.0
Perpendicular to grain, flatwise	$f_{c,90,flat,k}$	1.8	1.8
<u>Tension strength</u>			
Parallel to grain (length 3000mm)	$f_{t,0,k}$	28.0	30.0
Perpendicular to grain, edgewise	$f_{t,90,edge,k}$	3.0	2.5
Perpendicular to grain, flatwise	$f_{t,90,flat,k}$	NPD	NPD
<u>Shear strength</u>			
Edgewise	$f_{v,0,edge,k}$	4.1	4.1
Flatwise, parallel to grain	$f_{v,0,flat,k}$	1.3	1.3
Flatwise, perpendicular to grain	$f_{v,90,flat,k}$	NPD	NPD
Density			
Density, mean value	ρ_{mean}	510	510
Density, fifth percentile value	ρ_k	480	480

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

¹ In service class 2 the values 28.0 N/mm² and 30.0 N/mm² is recommended to be divided by 1.2

² Covering $E_{m,0,edge,mean}$, $E_{t,0,mean}$, and $E_{c,0,mean}$

³ Covering $E_{m,0,edge,k}$, $E_{t,0,k}$, and $E_{c,0,k}$

⁴ Covering $E_{t,90,edge,mean}$

⁵ Covering $E_{t,90,edge,k}$

ESSENTIAL CHARACTERISTICS	PERFORMANCE			
Bonding quality	requirement fulfilled			
Reaction to fire	End use condition	Minimum thickness (mm)	Class (excluding floorings)	Class (floorings)
	- any substrate or air gap behind the product	39	D-s2, d0	Dfl-s1
	- with or without an air gap between the product and a substrate of class A1 or A2-s1,d0, thickness of at least 6 mm and density of at least 800 kg/m ³ - fixed mechanically to wooden or metallic frames	39	D-s1, d0	-
	- free standing applications	39	D-s1, d0	-
Release of formaldehyde	E1			
Natural durability against biological attack (EN 350-2)	Class 5 (includes sapwood)			

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Espoo on 10.7.2023

Sakari Kainumaa
 Director, Product Management
 Metsä Wood



Juha Kasslin
 SVP, Supply Chain Management
 Metsä Wood

