

DECLARATION OF PERFORMANCE

NO. MW/LVL/318-001/CPR/DOP



1. PRODUCT-TYPE:

Kerto LVL L-panel
Structural Laminated Veneer Lumber

2. INTENDED USES:

Buildings and bridges

3. MANUFACTURER:

Metsäliitto Cooperative
Metsä Wood
P.O.Box 24
FI-08101 Lohja, Finland
Tel. +358 10 4656 499
www.metsawood.com

5. SYSTEM OF ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE:

AVCP System 1

6a. HARMONISED STANDARD:

EN 14374:2004

Notified body:

Eurofins Expert Services Oy, Notified product certification body No. 0809

Certificate of constancy of performance:

0809 – CPR – 1002

7. DECLARED PERFORMANCES

ESSENTIAL CHARACTERISTICS	SYMBOL	PERFORMANCE	
		KERTO-L THICKNESS 21 - 24 mm	KERTO-L THICKNESS 27 - 75 mm
Modulus of elasticity and shear modulus		N/mm² or kg/m³	N/mm² or kg/m³
<u>Modulus of elasticity, mean values</u>			
Parallel to grain, along	$E_{0,mean}$	6700	7500
Parallel to grain, across	$E_{90,mean}$	700	1300
Perpendicular to grain, edgewise	$E_{90,edge,mean}$	1700	1700
Perpendicular to grain, flatwise	$E_{90,flat,mean}$	NPD	NPD
<u>Modulus of elasticity, fifth percentile value</u>			
Parallel to grain, along	$E_{0,k}$	5500	6500
Parallel to grain, across	$E_{90,k}$	600	1100
Perpendicular to grain, edgewise	$E_{90,edge,k}$	1400	1400
Perpendicular to grain, flatwise	$E_{90,flat,k}$	NPD	NPD
<u>Shear modulus, mean values</u>			
Edgewise	$G_{0,edge,mean}$	500	500
Flatwise, parallel to grain	$G_{0,flat,mean}$	70	70
Flatwise, perpendicular to grain	$G_{90,flat,mean}$	18	18
<u>Shear modulus, fifth percentile value</u>			
Edgewise	$G_{0,edge,k}$	330	330
Flatwise, parallel to grain	$G_{0,flat,k}$	55	55
Flatwise, perpendicular to grain	$G_{90,flat,k}$	14	14
Strength, fifth percentile values			
<u>Bending strength</u>			
Edgewise (depth 300mm)	$f_{m,0,edge,k}$	19.0	20.5
Size effect parameter	s	0.15	0.15
Flatwise, parallel to grain	$f_{m,0,flat,k}$	22.5	25.0
Flatwise, perpendicular to grain	$f_{m,90,flat,k}$	5.5	6.5
<u>Compression strength</u>			
Parallel to grain	$f_{c,0,k}$	18.0 ¹	19.0 ¹
Perpendicular to grain, edgewise	$f_{c,90,edge,k}$	8.0	8.0
Perpendicular to grain, flatwise	$f_{c,90,flat,k}$	2.0	2.0
<u>Tension strength</u>			
Parallel to grain (length 3000mm)	$f_{t,0,k}$	15.0	17.0
Perpendicular to grain, edgewise	$f_{t,90,edge,k}$	4.0	4.0
Perpendicular to grain, flatwise	$f_{t,90,flat,k}$	NPD	NPD
<u>Shear strength</u>			
Edgewise	$f_{v,0,edge,k}$	4.0	4.0
Flatwise, parallel to grain	$f_{v,0,flat,k}$	1.2	1.2
Flatwise, perpendicular to grain	$f_{v,90,flat,k}$	0.5	0.5
Density			
Density, mean value	ρ_{mean}	440	440
Density, fifth percentile value	ρ_k	410	410

¹ In service class 2 the values 18.0 N/mm² and 19.0 N/mm² are recommended to be divided by 1.2. The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

ESSENTIAL CHARACTERISTICS	PERFORMANCE			
Bonding quality	requirement fulfilled			
Reaction to fire	End use condition	Minimum thickness (mm)	Class (excluding floorings)	Class (floorings)
	- any substrate or air gap behind the product	21	D-s2, d0	Dfl-s1
	- with or without an air gap between the product and a substrate of class A1 or A2-s1, d0, thickness of at least 6 mm and density of at least 800 kg/m ³ - fixed mechanically to wooden or metallic frames	27	D-s1, d0	-
Release of formaldehyde	E1			
Natural durability against biological attack (EN 350-2)	Class 5 (includes sapwood)			

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Espoo on 2.1.2022

Henrik Söderström
SVP, Supply Chain Management
Metsä Wood



Juha Kasslin
VP, Product Management
Metsä Wood

