

# UK DECLARATION OF CONFORMITY

NO. MW/LVL/318-001/UKCA/UKDOC



**1. PRODUCT-TYPE:**

Kerto LVL L-panel

Structural Laminated Veneer Lumber, with crosswise veneers (LVL-C)

NOMINAL THICKNESS	NUMBER OF VENEERS	LONG GRAINED	CROSS GRAINED	LAY-UP
21 mm	7	5	2	—   —
21 mm	7	5	2	— —
24 mm	8	6	2	—  —
27 mm	9	7	2	—   —
30 mm	10	8	2	—    —
33 mm	11	9	2	—     —
39 mm	13	10	3	—   —   —
45 mm	15	12	3	—    —   —
51 mm	17	14	3	—     —   —
57 mm	19	15	4	—   —    —   —
63 mm	21	16	5	—   —   —   —   —
69 mm	23	18	5	—    —   —   —   —
75 mm	25	20	5	—     —   —   —   —

**2. INTENDED USES:**

Buildings and bridges

**3. MANUFACTURER:**

Metsäliitto Cooperative  
Metsä Wood  
P.O.Box 24  
FI-08101 Lohja, Finland  
Tel. +358 10 4605  
[metsagroup.com/metsawood/](http://metsagroup.com/metsawood/)

**5. SYSTEM OF ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE:**

AVCP System 1

**6a. DESIGNATED STANDARD:**

EN 14374:2004

Approved body:  
CATG Ltd, No. 1245

Certificate of constancy of performance:  
1245-CPR-8002 (Lohja LVL mill)  
1245-CPR-8003 (Punkaharju LVL mill)

## 7. DECLARED PERFORMANCES

ESSENTIAL CHARACTERISTICS	SYMBOL	PERFORMANCE	
		KERTO LVL L-panel LVL 22 C THICKNESS 21 - 24 mm	KERTO LVL L-panel LVL 25 C THICKNESS 27 - 75 mm
<b>Modulus of elasticity and shear modulus</b>		<b>N/mm<sup>2</sup> or kg/m<sup>3</sup></b>	<b>N/mm<sup>2</sup> or kg/m<sup>3</sup></b>
<u>Modulus of elasticity, mean values</u>			
Parallel to grain, along	$E_{0,mean}^2$	6700	7500
Parallel to grain, across	$E_{m,90,flat,mean}$	700	1300
Perpendicular to grain, edgewise	$E_{c,90,edge,mean}^4$	1700	1700
Perpendicular to grain, flatwise	$E_{c,90,flat,mean}$	NPD	NPD
<u>Modulus of elasticity, fifth percentile value</u>			
Parallel to grain, along	$E_{0,k}^3$	5500	6500
Parallel to grain, across	$E_{m,90,flat,k}$	600	1100
Perpendicular to grain, edgewise	$E_{c,90,edge,k}^5$	1400	1400
Perpendicular to grain, flatwise	$E_{c,90,flat,k}$	NPD	NPD
<u>Shear modulus, mean values</u>			
Edgewise	$G_{0,edge,mean}$	500	500
Flatwise, parallel to grain	$G_{0,flat,mean}$	70	70
Flatwise, perpendicular to grain	$G_{90,flat,mean}$	18	18
<u>Shear modulus, fifth percentile value</u>			
Edgewise	$G_{0,edge,k}$	330	330
Flatwise, parallel to grain	$G_{0,flat,k}$	55	55
Flatwise, perpendicular to grain	$G_{90,flat,k}$	14	14
<b>Strength, fifth percentile values</b>			
<u>Bending strength</u>			
Edgewise (depth 300mm)	$f_{m,0,edge,k}$	19.0	20.5
Size effect parameter	$s$	0.15	0.15
Flatwise, parallel to grain	$f_{m,0,flat,k}$	22.5	25.0
Flatwise, perpendicular to grain	$f_{m,90,flat,k}$	5.5	6.5
<u>Compression strength</u>			
Parallel to grain	$f_{c,0,k}$	18.0 <sup>1</sup>	19.0 <sup>1</sup>
Perpendicular to grain, edgewise	$f_{c,90,edge,k}$	8.0	8.0
Perpendicular to grain, flatwise	$f_{c,90,flat,k}$	2.0	2.0
<u>Tension strength</u>			
Parallel to grain (length 3000mm)	$f_{t,0,k}$	15.0	17.0
Perpendicular to grain, edgewise	$f_{t,90,edge,k}$	4.0	4.0
Perpendicular to grain, flatwise	$f_{t,90,flat,k}$	NPD	NPD
<u>Shear strength</u>			
Edgewise	$f_{v,0,edge,k}$	4.0	4.0
Flatwise, parallel to grain	$f_{v,0,flat,k}$	1.2	1.2
Flatwise, perpendicular to grain	$f_{v,90,flat,k}$	0.5	0.5
<b>Density</b>			
Density, mean value	$\rho_{mean}$	440	440
Density, fifth percentile value	$\rho_k$	410	410

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

<sup>1</sup> In service class 2 the values 18.0 N/mm<sup>2</sup> and 19.0 N/mm<sup>2</sup> are recommended to be divided by 1.2

<sup>2</sup> Covering  $E_{m,0,edge,mean}$ ,  $E_{m,0,flat,mean}$ ,  $E_{t,0,mean}$ , and  $E_{c,0,mean}$

<sup>3</sup> Covering  $E_{m,0,edge,k}$ ,  $E_{m,0,flat,k}$ ,  $E_{t,0,k}$ , and  $E_{c,0,k}$

<sup>4</sup> Covering  $E_{t,90,edge,mean}$

<sup>5</sup> Covering  $E_{t,90,edge,k}$

ESSENTIAL CHARACTERISTICS	PERFORMANCE			
Bonding quality	requirement fulfilled			
Reaction to fire	End use condition	Minimum thickness (mm)	Class (excluding floorings)	Class (floorings)
	- any substrate or air gap behind the product	21	D-s2, d0	Dfl-s1
	- with or without an air gap between the product and a substrate of class A1 or A2-s1, d0, thickness of at least 6 mm and density of at least 800 kg/m <sup>3</sup> - fixed mechanically to wooden or metallic frames	27	D-s1, d0	-
Release of formaldehyde	E1			
Natural durability against biological attack (EN 350-2)	Class 5 (includes sapwood)			

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

The performance of the product identified above is in conformity with the set of declared performance/s. This UK declaration of conformity is issued, in accordance with Regulation 305/2011/EU as it has effect in the United Kingdom, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Espoo on 10.7.2023

Sakari Kainumaa  
Director, Product Management  
Metsä Wood



Juha Kasslin  
SVP, Supply Chain Management  
Metsä Wood

