

UK DECLARATION OF CONFORMITY

NO. MW/LVL/311-001/ UKCA/UKDOC



1. PRODUCT-TYPE:

Kerto LVL S-beam
Structural Laminated Veneer Lumber, only parallel veneers (LVL-P)

2. INTENDED USES:

Buildings and bridges

3. MANUFACTURER:

Metsäliitto Cooperative
Metsä Wood
P.O.Box 24
FI-08101 Lohja, Finland
Tel. +358 10 4605
metsagroup.com/metsawood/

5. SYSTEM OF ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE:

AVCP System 1

6a. DESIGNATED STANDARD:

EN 14374:2004

Approved body:
CATG Ltd, No. 1245

Certificate of constancy of performance:
1245-CPR-8002 (Lohja LVL mill)
1245-CPR-8003 (Punkaharju LVL mill)

7. DECLARED PERFORMANCES

| ESSENTIAL CHARACTERISTICS | SYMBOL | PERFORMANCE |
|--|------------------------|---|
| | | KERTO LVL S-beam LVL 48 P THICKNESS 21 - 90 mm |
| Modulus of elasticity and shear modulus | | N/mm² or kg/m³ |
| <u>Modulus of elasticity, mean values</u> | | |
| Parallel to grain, along | $E_{0,mean}^2$ | 13800 |
| Parallel to grain, across | $E_{m,90,flat,mean}$ | NPD |
| Perpendicular to grain, edgewise | $E_{c,90,edge,mean}^4$ | NPD |
| Perpendicular to grain, flatwise | $E_{c,90,flat,mean}$ | NPD |
| <u>Modulus of elasticity, fifth percentile value</u> | | |
| Parallel to grain, along | $E_{0,k}^3$ | 11600 |
| Parallel to grain, across | $E_{m,90,flat,k}$ | NPD |
| Perpendicular to grain, edgewise | $E_{c,90,edge,k}^5$ | NPD |
| Perpendicular to grain, flatwise | $E_{c,90,flat,k}$ | NPD |
| <u>Shear modulus, mean values</u> | | |
| Edgewise | $G_{0,edge,mean}$ | 600 |
| Flatwise, parallel to grain | $G_{0,flat,mean}$ | 380 |
| Flatwise, perpendicular to grain | $G_{90,flat,mean}$ | NPD |
| <u>Shear modulus, fifth percentile value</u> | | |
| Edgewise | $G_{0,edge,k}$ | 400 |
| Flatwise, parallel to grain | $G_{0,flat,k}$ | 270 |
| Flatwise, perpendicular to grain | $G_{90,flat,k}$ | NPD |
| Strength, fifth percentile values | | |
| <u>Bending strength</u> | | |
| Edgewise (depth 300mm) | $f_{m,0,edge,k}$ | 44.0 |
| Size effect parameter | S | 0.12 |
| Flatwise, parallel to grain | $f_{m,0,flat,k}$ | 50.0 |
| Flatwise, perpendicular to grain | $f_{m,90,flat,k}$ | NPD |
| <u>Compression strength</u> | | |
| Parallel to grain | $f_{c,0,k}$ | 35.0 ¹ |
| Perpendicular to grain, edgewise | $f_{c,90,edge,k}$ | 6.0 |
| Perpendicular to grain, flatwise | $f_{c,90,flat,k}$ | 2.2 |
| <u>Tension strength</u> | | |
| Parallel to grain (length 3000mm) | $f_{t,0,k}$ | 35.0 |
| Perpendicular to grain, edgewise | $f_{t,90,edge,k}$ | 0.8 |
| Perpendicular to grain, flatwise | $f_{t,90,flat,k}$ | NPD |
| <u>Shear strength</u> | | |
| Edgewise | $f_{v,0,edge,k}$ | 4.2 |
| Flatwise, parallel to grain | $f_{v,0,flat,k}$ | 2.3 |
| Flatwise, perpendicular to grain | $f_{v,90,flat,k}$ | NPD |
| Density | | |
| Density, mean value | ρ_{mean} | 510 |
| Density, fifth percentile value | ρ_k | 480 |

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

¹ In service class 2 the value 35.0 N/mm² is recommended to be divided by 1.2

² Covering $E_{m,0,edge,mean}$, $E_{m,0,flat,mean}$, $E_{t,0,mean}$, and $E_{c,0,mean}$

³ Covering $E_{m,0,edge,k}$, $E_{m,0,flat,k}$, $E_{t,0,k}$, and $E_{c,0,k}$

⁴ Covering $E_{t,90,edge,mean}$

⁵ Covering $E_{t,90,edge,k}$

| ESSENTIAL CHARACTERISTICS | PERFORMANCE | | | |
|---|---|------------------------|-----------------------------|-------------------|
| Bonding quality | requirement fulfilled | | | |
| Reaction to fire | End use condition | Minimum thickness (mm) | Class (excluding floorings) | Class (floorings) |
| | - any substrate or air gap behind the product | 21 | D-s2, d0 | Dfl-s1 |
| | - with or without an air gap between the product and a substrate of class A1 or A2-s1,d0, thickness of at least 6 mm and density of at least 800 kg/m ³ - fixed mechanically to wooden or metallic frames | 27 | D-s1, d0 | - |
| | - free standing applications | 27 | D-s1, d0 | - |
| Release of formaldehyde | E1 | | | |
| Natural durability against biological attack (EN 350-2) | Class 5 (includes sapwood) | | | |

The material values in this DoP are to be used for structural calculations with EN 1995 (Eurocode 5).

The performance of the product identified above is in conformity with the set of declared performance/s. This UK declaration of conformity is issued, in accordance with Regulation 305/2011/EU as it has effect in the United Kingdom, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Espoo on 10.7.2023

Sakari Kainumaa
Director, Product Management
Metsä Wood



Juha Kasslin
SVP, Supply Chain Management
Metsä Wood

